

Product Specifications

Recycled Polyethylene Terephthalate (PET) Resin

Cylindrical recycled PET granules

Property	Specs	Test Method
IV (dl/g)	0.50 ± 0.05	ASTM D 1238
Bulk Density (kg/m ³)	800 ± 50	BQ/QC-03
Particle Size (pcs/g)	60-100	BQ/QC-04
Moisture	< 1 %	ASTM D 6980
Dust	< 1%	BQ/QC-05
Melting Point (°C)	249°C (±) 6	

